



# Krytox<sup>®</sup>

performance lubricants

## Krytox<sup>®</sup> LVP High-Vacuum Grease

***Performs Dependably—No Matter What Conditions Your System Operates Under***

Low pressures. Extremely high or low temperatures. Hostile environments. Whatever special needs your system might have, Krytox<sup>®</sup> LVP high-vacuum grease works—safely, reliably, and cost-effectively.

Krytox<sup>®</sup> low vapor pressure (LVP) high-vacuum grease performs over extremes of temperature and pressure that hydrocarbon, silicone, and chlorofluorocarbon greases can't match. From  $-15$ – $300^{\circ}\text{C}$  ( $0$ – $570^{\circ}\text{F}$ ), at vapor pressures as low as  $10^{-13}$  mmHg, and in even the most chemically severe environments, Krytox<sup>®</sup> LVP grease gives dependable, proven performance.

Additionally, Krytox<sup>®</sup> LVP high-vacuum grease is nonflammable, insoluble, and chemically inert. It is also an excellent lubricant and sealant. And Krytox<sup>®</sup> LVP grease offers all these features at a price that is less expensive than many hydrocarbon, silicone, and chlorofluorocarbon greases.

Krytox<sup>®</sup> LVP high-vacuum grease is used as a sealant or lubricant in vacuum systems. Chemically inert and offering superior lubrication properties, Krytox<sup>®</sup> LVP grease combines the extremely low vapor pressure of Krytox<sup>®</sup> fluorinated oil, which is based on the most stable type of perfluoroalkylpolyether available, with a fluorocarbon thickener. Thus, Krytox<sup>®</sup> LVP grease will not explode, ignite, decompose, react to form gummy or solid deposits, or act as fuel for fires. Krytox<sup>®</sup> grease retains its lubricating ability at temperature extremes ranging from  $-15$ – $300^{\circ}\text{C}$  ( $0$ – $570^{\circ}\text{F}$ ) and offers complete oxidation resistance. All these features add up to lower wear and longer life for equipment and components—so important when access for component repair or replacement is difficult or impossible.

Krytox<sup>®</sup> fluorinated grease was first used as a highly reliable, low-friction lubricant in aerospace projects, such as the Lunar Rover's traction motors. It was in this and other similar critical applications that Krytox<sup>®</sup> lubricants earned a reputation for superior performance.

Today, DuPont's Krytox<sup>®</sup> products are proven performers that are setting the industry standard for safety, reliability, and cost-effectiveness.

### Typical Properties

Property	Value
NLGI Consistency	Grade 2 penetration
Vapor Pressure	
Torr at $20^{\circ}\text{C}$ ( $68^{\circ}\text{F}$ )	$-1.0 \times 10^{-13}$
Torr at $200^{\circ}\text{C}$ ( $392^{\circ}\text{F}$ )	$-1.0 \times 10^{-5}$
kPa at $20^{\circ}\text{C}$ ( $68^{\circ}\text{F}$ )	$-1.0 \times 10^{-14}$
kPa at $200^{\circ}\text{C}$ ( $392^{\circ}\text{F}$ )	$-1.0 \times 10^{-6}$
Evaporation Loss, $4 \times 10^{-6}$ torr at $150^{\circ}\text{C}$ ( $302^{\circ}\text{F}$ )	
(30 min) wt%	0.1
(60 min) wt%	0.2
(120 min) wt%	0.2
Evaporation Loss, 22 hr at $200^{\circ}\text{C}$ ( $392^{\circ}\text{F}$ )	<0.3%
Density, $25^{\circ}\text{C}$ ( $77^{\circ}\text{F}$ ), g/cc	1.94

This table gives typical properties based on historical production performance. DuPont does not make any express or implied warranty that this product will continue to have these typical properties.

## Applications

- Sealant or lubricant in vacuum systems
- High-temperature bearing, valve, and O-ring lubricant
- Oven conveyor chain and bearing grease
- Pressure relief valve lubricant
- Any use that requires high-temperature stability, low vapor pressure, or chemical inertness

## Chemically Inert

Krytox® LVP high-vacuum grease has demonstrated an exceptionally high degree of chemical inertness to many highly reactive chemicals. For example, Krytox® LVP grease shows no evidence of reactivity when exposed to:

- Boiling sulfuric acid
- Fluorine gas at 200°C (392°F)
- Chlorine trifluoride at 10–50°C (50–122°F)
- Uranium hexafluoride gas at 50°C (122°F)
- Molten sodium or potassium hydroxide at 318–360°C (605–680°F)
- Hydrogen gas at 250°C (482°F) and 250 psi
- Ammonia gas at 250°C (482°F) and 50 psi

The grease is not reactive with any of the following materials when tested at room temperature:

- Ethyl alcohol
- Hydrazine

- Diethylenetriamine
- 90% hydrogen peroxide
- Nitrogen tetroxide
- JP-4 turbine fuel
- Unsymmetrical dimethyl hydrazine
- Aniline
- Inhibited red fuming nitric acid
- Halogen acids
- Chlorine or bromine

## Nonflammable

Krytox® LVP grease is nonflammable under all conditions likely to be encountered in service. It shows no autogenous ignition, flash, or fire points up to the highest temperature tested, 649°C (1200°F), in standard ASTM tests.

## Compatible with Oxygen

At elevated temperatures and pressures, Krytox® LVP high-vacuum grease is highly resistant to attack by gaseous and liquid oxygen. As a result, it is the lubricant of choice in industries that manufacture or use oxygen.

Tests confirming the nonreactivity of Krytox® lubricants with oxygen were performed at a variety of conditions.

---

**For more information or technical assistance, visit us on the Web: [www.krytox.com](http://www.krytox.com)**

---

Or call the Krytox® hotline in the **United States** at (800) 424-7502, E-mail: [krytox@usa.dupont.com](mailto:krytox@usa.dupont.com)

**Canada** at 800-263-5924, E-mail: [products@can.dupont.com](mailto:products@can.dupont.com)

**Europe, Mideast, and Africa** at +32.3.543.1267, E-mail: [lubricants@lux.dupont.com](mailto:lubricants@lux.dupont.com)

**Asia/Pacific—Including India** at 886-2-2514-4434, E-mail: [krytox.lubricants@twm.dupont.com](mailto:krytox.lubricants@twm.dupont.com)

**Mexico and Central America** at +52-5-722-1150, [www.dupont.com.mx](http://www.dupont.com.mx)

**South America—All Countries** at 55-11-4166-8601, E-mail: [produtos.brasil@bra.dupont.com](mailto:produtos.brasil@bra.dupont.com)

---

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill and at their own discretion and risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

Copyright © 2000 E.I. du Pont de Nemours and Company. All rights reserved.



**Krytox®**  
performance lubricants